

XIAMETER[®] OFS-6020 Silane

Diaminofunctional silane

FEATURES

- Coupling agent
- Improved adhesion
- Increased wet and dry tensile strength and modulus to the composite
- Increased wet and dry flexural strength and modulus to the composite
- Increased wet and dry compressive strength
- Improved compatibility between inorganic filler and organic polymer

APPLICATIONS

- XIAMETER[®] OFS-6020 Silane has been found to be an effective coupling agent for clay reinforced elastomers such as natural and nitrile rubber. The silane-treated clay provides improvement in both physical and dynamic properties compared to similar cured elastomers containing untreated clay.
- XIAMETER OFS-6020 Silane has been reported to be an effective coupling agent for mineral reinforced nylon 6, nylon 6/6 and polybutyleneterephthalate
- Fiberglass reinforced phenolic, melamine and epoxy thermoset composites, either as fiberglass finish or as resinous additive.
- As an additive to improve the performance of these types of thermoset resins when they are used as mineral binders in foundry and abrasive composite applications.
- Coupling agent for phenolic, melamine and other organic resins used as binders for glass and mineral wood insulation, abrasives and molding components.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local XIAMETER[®] sales representative prior to writing specifications on this product.

Test	Unit	Value
Appearance		Clear liquid
Flash point – closed cup	°C (°F)	85 (185)
Specific Gravity at 25°C (77°F)		1.03
Refractive index		1.445
Neutral equivalents	g/eq	115
Color		Light straw
Viscosity	mm ² /s	5

DESCRIPTION

XIAMETER OFS-6020 Silane possesses both organic and inorganic reactivity. XIAMETER OFS-6020 Silane can react with organic polymers and glass or other inorganic mineral surfaces.

of additive should be determined by testing several concentrations. When used as an additive to epoxy coatings, this product improves adhesion of the coating, particularly in a very humid environment.

HOW TO USE

When used as a resin additive, generally the silane is added at a level of less than 1% based on the weight of the resin solids. For each specific application, the optimum level

XIAMETER OFS-6020 Silane can be applied to inorganic surfaces, like other silanes, as a dilute aqueous solution (0.1% to 0.5%) silane concentration). Aqueous solutions can be prepared by simply adding the silane to water with stirring.

However, poor agitation when adding XIAMETER OFS-6020 Silane to water can result in locally high concentration which may form gel particles. It is normally recommended that the silane solution be acidified to a pH of 3.0 to 4.5 with an organic acid, such as acetic acid, to obtain optimum performance of reinforcing material such as fiberglass.

Inorganic surfaces can be treated with the aqueous solution by either dipping or padding. In the case of siliceous mineral fillers, the mineral can be treated by slurring in the aqueous solution or mixed with the silane at very high shear without any additional solvent.

After applying the silane, the glass or mineral surface can be air dried or dried briefly at 105° to 120°C (221° - 248°F) to effect complete condensation of silanol groups at the surface and to remove water and/or traces of methanol. Optimum application and drying conditions, such as time and temperature, should be determined for each application prior to use in a commercial process.

PRODUCT SAFETY INFORMATION

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL, ENVIRONMENTAL, AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE XIAMETER® WEB SITE AT WWW.XIAMETER.COM.

STORAGE

Product should be stored at or below 25°C (77°F) in original, unopened containers. The most up-to-date shelf life information can be found on the XIAMETER Web site in the Product Detail page under Sales Specification.

Keep away from heat and open flame.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses. Not intended for human injection. Not intended for food use.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.